

FINAL UNIVERSAL SILICONE TUPE

One-component acetoxy cure silicone sealant for a range of general sealing and glazing applications.

PROPERTIES

- Stays permanently elastic after curing.
- Remains flexible in low and high temperatures.
- Resistant to temperature extremes.
- Resistance to aging, cracking and discoloring.

APPLICATION AREAS

- Sealing around windows and doors.
- Sealing in DIY applications.
- On bathroom, kitchen and plumbing applications.
- Connection and expansion joints on glass, porcelain, steel etc.
- Sealing electric, telephone etc. sockets and switches.

SILICONE ADVANTAGES

- Silicone sealants outperform and outlast organic weatherproofing sealants.
- Silicone sealants have greater UV stability and temperature and weather resistance than organic sealants.
- Silicone sealants are inherently waterproof.
- Silicone sealants remain flexible over a wide temperature range (-40 to 150°C) and are easy to apply in cold weather.
- Silicone sealants last longer and need to be replaced less often than many organic sealants, which reduces lifetime costs and contributes to sustainability.

SURFACE PREPARATION

Following cleaning procedure and materials are recommended:

| | |
|--|--|
| Glass | Degrease with alcohol or MEK |
| Aluminum, light alloys and stainless steel | Degrease with alcohol or MEK |
| Other Metals | Lightly abrade then degrease as above |
| Wood | Lightly abrade surface then remove dust |
| Plastics | Degrease using an agent recommended by plastics manufacturer |

STORAGE AND SHELF LIFE

The shelf life is 18 months if stored in unopened-original package in a dry place at temperatures between +5°C and +25°C.

COLORS

Transparent-White-Black

PACKAGING OPTIONS

30gr tupe / 48box

SAFETY & DISPOSAL

Inhalation of the sealant vapor for a long period must be avoided. The application area must be ventilated properly. The uncured sealant must not be contacted for a long period. Cured silicone rubber bears no risk to health. Temperatures between +5°C and +25°C. Check MSDS guidelines for disposal and further information concerning safety.

WARNING

- It must not be used in totally confined spaces where sealant cannot cure due to lack of atmospheric moisture.
- Not recommended to use on porous surfaces like marble, natural stone, concrete etc.
- Because of acidic curing, it must not be used on mirrors and sensitive metals like copper, brazen, lead. Not over paintable.
- Do not use in conjunction with bitumen asphalt, neoprene and certain organic elastomers.
- It is not suitable for food contact applications.
- Do not contact with water.
- Avoid from direct UV.
- Can yellow if exposed to bleach or HCL based brick cleaners whilst curing.

PRODUCT INFORMATION

| Product Name | Composition | Typical Applications | Available Colors |
|--------------------------|--|--|---------------------------|
| Acetoxy Sealants | | | |
| SLT-5431 Sealant Acetoxy | Acetoxy; one-component; RTV silicone sealant | Suitable for sanitary or other sealing applications where mildew resistance of the cured sealant is required | White, transparent, black |



CHASBKARAN SAHELE ARAS CO.

TECHNICAL DATA SHEET

TYPICAL PROPERTIES

| Product Name | Tack-free time, min | Flow, mm | Extrusion, g/min | Depth cure, mm/day | Durometer, Shore A, points | Density, g/cm ³ | Elongation, % | Tensile, MPa |
|--------------------------------|---------------------|----------|------------------|--------------------|----------------------------|----------------------------|---------------|--------------|
| Acetoxy Sealants | | | | | | | | |
| SLT-5431 Sealant Acetoxy | - | - | 817 | 1.8 | 13 | 0.96-0.98 | 480 | 2.1 |